



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

WOOL

3R2900



Description

Made from pure mullite fibers only, needled on both sides. It can be used at continuous operating temperatures up to 1600°C (2912°F), under oxidizing, neutral or slightly gas-rich atmospheres, retaining their original toughness, strength and soft fibrous structure after extended use at these temperatures.

Applications

It is an excellent choice for insulation and refractory support.

Specifications

Technical Data

Temperature	1600°C (2912°F)
Composition	Alumina: 80%, Silica: 19%

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.