



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

FIBERGLASS

3R3144SIL



Description

Made with fiberglass carded yarns and viscose fiber. This fabric is designed for high temperature applications.

Applications

The 3R 3144SIL can be used to make protective curtains, insulation mattresses and expansion joints.

Specifications

Technical Data

Color	Green
Composition	HT carded fiberglass: 75 to 85%, Viscose fiber : 15 to 25%
Temperature	Fiberglass: 1000°C (1832°F), Viscose: 150 to 220°C (302 to 428°F)
Thickness	0.10"
Width	40"
Weight	41 oz/yd ²
UV Resistance	Good
Acid Resistance	Medium (except HN03)
Alkali resistance	Low

Solvent Resistance

Good (except DMF)

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.