



INDUSTRIES 3R

**Danville Office**  
55, route 116 Ouest  
Danville (Québec) Canada  
J0A 1A0

Phone: 819-839-2793  
Fax: 819-839-2797  
Toll-free: 800-567-2728  
E-mail: info@industries3r.com

NEOPRENE

## 3R815LC



### Description

The 3R815LC offers similar specifications found in the top quality 3R815 neoprene rubber. It can be used in many applications where less particularities are required. It is provided in three different durometers.

### Applications

This material can be used as flange gasketing and as static joints. It is also used in applications where the material is in contact with harsh atmospheric conditions.

### Specifications

#### Technical Data

Polymer	CR
Color	Black
Hardness (Shore A) ± 5	60
Temperature	-25°C to 85°C (-10°F to 185°F)
Tensile Strength	500psi nom.
Elongation	300% min.
Compression Set	Good
Abrasion Resistance	Good
Tear Resistance	Good
Ozone Resistance	Fair

Impermeability to Gases	Fair to Good
Resistance to Dilute Acid	Fair
Résistance to aromatic hydro-carbons	Fair
Heat Aging	Fair

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.