



INDUSTRIES 3R

Danville Office

55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793

Fax: 819-839-2797

Toll-free: 800-567-2728

E-mail: info@industries3r.com

NEOPRENE

3R818



Description

This rubber is made with one or four thicknesses of polyester fabric inserted in a premium quality neoprene. The 3R818 combines the oil and ozone resistance to resistance of the synthetic fabric. It offers exceptional tensile strength.

Applications

- Gaskets for control valves and regulators
- Cold barriers

Specifications

Technical Data

| | |
|------------------------------------|--------------------------------------|
| Polymer | Neoprene, Styrene-Butadiene (CR/SBR) |
| Fabric | Nylon 14 oz. |
| Color | Black |
| Specific Gravity | 1.58 gr/cc |
| Hardness (Shore A) (ASTM D2240) | 70 |
| Tensile, psi (ASTM D412) | 1400 min. |
| Ultimate Elongation, % (ASTM D412) | 250 min. |
| Temperature | -29°C to 100°C (-20°F to 212°F) |
| Compression Set (D395B) | 22 hrs @ 100C (212F): 35% max. |

| | |
|--------------------------------------|--|
| Heat Aging (ASTM D573) | 70 hrs @ 100C (212F) - Changed: Hardness + 15 points max., Tensile -15% max., Elongation -40% max. |
| Oil Aging #3 (ASTM D471) | 70 hrs @ 100C (212F) - Changed: Hardness +/- 10 points max., Tensile: -70% max., Elongation: -55% max., Volume: +120% max. |
| Abrasion resistance | Good |
| Tear Resistance | Good |
| Ozone Resistance | Good |
| Impermeability to Gases | Good |
| Resistance to Dilute Acid | Good |
| Resistance to aromatic hydro-carbons | Good |
| Heat Aging | Good |

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.