



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

DURASHIELD

3R857



Description

Red Durashield rubber offers a high resistance to abrasion and tear. The 3R857 can withstand the most severe abrasive industrial applications better than other rubbers would.

Applications

- Mines
- Material handling hoses
- Chute linings

Specifications

Technical Data

Polymer	Natural Rubber (NR)
Color	Red
Hardness (Shore A) (ASTM D2240)	40 ± 5
Density	1.06 gr/cm ³
Temperature	-40°C to 82°C (-40°F to 180°F)
Tensile (ASTM D412)	3000 psi min.
Ultimate Elongation (ASTM D412)	600% min.
Tear (ASTM D624)	350 lbs/in

Abrasion resistance (DIN 53516)	Wet: 40mm ³ , Dry: 160mm ³
Compression Set (ASTM D395B)	22 hrs @ 70C (158F): 25% max.
Heat Aging (ASTM D573)	70 hrs @ 70C (158F) - Changed: Hardness: + 10 points max., Tensile: - 25% max., Elongation: -25% max.
Tear Resistance	Outstanding
Ozone Resistance	Poor
Impermeability to Gases	Good
Resistance to Dilute Acid	Fair
Resistance to aromatic hydro-carbons	Poor
Heat Aging	Fair

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.