



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

DURASHIELD

3R858



Description

Dura-Shield rubber offers a high resistance to cut, tear and abrasion. It reduces impacts and vibration. Moreover, the 3R858 has a surface that eases adhesion. It can withstand the most severe abrasive industrial applications better than other rubbers would.

Applications

- Abrasion where installation needs gluing
- Mines
- Chute linings

Specifications

Technical Data

Polymer	Natural NR
Color	Red
Density	1.06 gr/cc
Hardness (Shore A) ± 5	40
Temperature	-40°C to 82°C (-40°F to 180°F)
Tensile Strength (ASTM D412)	3000 psi min
Elongation (ASTM D412)	600% min.
Tear (ASTM D624)	350 lbs/in ²

Abrasion (DIN 53516)	Wet: 40 mm ³ , Dry: 160 mm ³
Compression set (ASTM D395B)	22 hrs @ 70C (158F): 25% max.
Heat aging	70h @ 70C (158F): Changed - Hardness : + 10 pts max., Tensile : - 25% max., Elongation: -25% max.
Compression Set	Excellent
Abrasion Resistance	Outstanding
Tear Resistance	Outstanding
Ozone Resistance	Poor
Impermeability to Gases	Good
Resistance to Dilute Acid	Fair
Resistance to aromatic hydro-carbons	Poor
Heat Aging	Fair

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.