



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

GRAPHITE SHEETS

3R887T



Description

The 3R 887T is a flexible graphite sheet reinforced with a 0.005" thick 316ss tanged core. This sheet is made from exfoliated graphite flakes which is compressed into a foil by a carefully controlled calendering process. In this process, the expanded flake particles are mechanically locked together without the use of fibers, binders or other additives. Sheets of foil are then adhesively bonded and laminated to the required thickness.

Applications

The 3R 887T flexible graphite sheet has pressure-temperature sealing capabilities that are far superior to all asbestos and non-asbestos reinforced sheet products. It is resistant to chemical attacks by virtually all organic and inorganic fluids with the exception of concentrated, highly oxidizing acids.

Gaskets cut from this sheet seal low to moderate bolt loads and because of its very low creep relaxation, re-torquing is rarely required. Flexible graphite readily flows into flange irregularities enabling it to seal both smooth and coarse surface finishes.

Specifications

Technical data

Temperature In air	-240°C à 510°C (-400°F à 950°F)
Temperature Mild oxidizing environnement	-240°C à 850°C (-400°F à 1500°F)
Temperature Non oxidizing environnement	980°C (1800°F)
Compressibility (ASTM F-36)	37%
Recovery (ASTM F-36)	18%
Creep Relaxation (ASTM F-38)	Less than 5%

Chemical Composition	Carbon: 99% min., Ash: 0.8% max., Leachable chloride: 30 ppm max.
Thickness	1/32", 1/16", 1/8"
Sizes	39.4" X 39.4", 60" X 60 "

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.