



INDUSTRIES 3R

Danville Office
55, route 116 Ouest
Danville (Québec) Canada
J0A 1A0

Phone: 819-839-2793
Fax: 819-839-2797
Toll-free: 800-567-2728
E-mail: info@industries3r.com

FELT

3R900



Description

The 3R900 felt is made from wool and synthetic fibers. It is available in rolls, strips and customized die cut forms.

Applications

This felt is rigid and resists to friction. It is used where light oil distribution is present. It is also used as ink rollers, plugs and buffers.

Specifications

Technical Data

Composition	Wool: 95% min.
Density	1" thick: 16.00 lbs/yd ²
Color	White
Specific Gravity	0.342
Temperature	-60°C to 90°C (-80°F to 200°F)
Absorption by weight (1.0 Sp. Gr. Liquid)	> 175%
Abrasion Resistance	Excellent
Resistance to dilute acids	Excellent
Resistance to alkalis	Fair
Resistance to oils & solvents	Excellent
Thickness	1/8", 3/16", 1/4", 3/8", 1/2", 3/4", 1"

N.B. The information presented may differ from practice. We recommend conducting tests according to the conditions of use. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products. The data is subject to certain variations without notice.